

TEST REPORT

No.: XMIN2608002202CM01_EN

Issue Date: 2026-09-03

Page: 1 of 3

CUSTOMER NAME: RAMHOUSE, LLC

ADDRESS: RUSSIA, 115487, MOSCOW, NAGATINSKAYA ST., BUILDING 16,
HOUSING 1, CONSTRUCTION 5, ROOM 6H

Sample Name : MSPC Laminate Floor by Stone Floor

Product Specification : Thickness: 8.3+/- 1mm

Other Information : Product Description: Mineral Stone Polycomposite (MSPC)

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Sample Source : Customer-delivered

Date of Receipt : 2026-08-27

Testing Period : 2026-08-27 ~ 2026-09-03

Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co.,Ltd. Xiamen Branch

Bryan

Bryan Hong

Authorized signatory

Scan to see the report



XMIN2608002202CM01
Verification:
check.sgsonline.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5765857 www.sgsgroup.com.cn
t (86-592) 5765857 sgs.china@sgs.com

TEST REPORT

No.: XMIN2608002202CM01_EN

Issue Date: 2026-09-03

Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result
1	Bending Strength and Modulus of Elasticity	GB/T 17657-2022 Section 4.7	Bending Strength: 43.9 MPa Modulus of Elasticity: 6560 MPa

Original Sample Photo:



SGS-CTC Standards Technical Services Co., Ltd.
Xiamen Branch

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5765857 www.sgsgroup.com.cn
t (86-592) 5765857 sgs.china@sgs.com

TEST REPORT

No.: XMIN2608002202CM01_EN

Issue Date: 2026-09-03

Page: 3 of 3

1.Test Item: Bending Strength and Modulus of Elasticity

Sample Description: See photo

Test Method: GB/T 17657-2022 Section 4.7

Test Condition:

Specimen: 210mm×50mm×8mm

Span: 160mm

Test speed: 4mm/min

Test Result:

Test Item	Test Result
Bending Strength	43.9 MPa
Modulus of Elasticity	6560 MPa

Note: All test specimens were cut from the sample.

*****End of report*****



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Xiamen Branch

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5765857 www.sgsgroup.com.cn
t (86-592) 5765857 sgs.china@sgs.com